



December 19, 2005

RE: TechLite Foam and Fungus Resistance

Tested to ASTM standard G-21 (Resistance of Synthetic Polymeric Materials to Fungi)

TechLite foam passes the ASTM-G 21 fungus growth test. VTEC laboratories Inc. in Bronx, New York tested the foam per the ASTM guidelines. Three samples were inoculated with fungus specimens and incubated in the proper growing conditions for a period of 7, 14 and 21 days. Growth ratings below are on a # 0-10 scale with a # 0 representing no growth detected.

After 7 days no samples showed any signs of fungus growth. (Rating # 0)

After 14 days no samples showed any signs of fungus growth. (Rating # 0)

After 21 days one sample indicated a trace of growth. (Rating # 1)

Please call if you have any other questions.

Thank you,
Dave Wenzlick
Engineer
TechLite® Insulation

Accessible Products Company
2122 W. 5th Place
Tempe AZ 85281

480-967-8888 480-894-6255 F www.techlite.net